# PARAPHALT LIQUID



# **CHARACTERISTICS**

- Semi-liquid coating, on the basis of bitumen, rubber and polymers
- For the making waterproof and renovation of roofs and guttering
- Also adheres to wet surfaces
- Applied cold

### **APPLICATIONS**

- Sealing, protection, renovation and maintenance of roofing, zinc, asbestos cement and corrugated plates
- Sealing of foundations
- Corrosion-resistance for metal surfaces
- Protection of piping. (Note : insulation can be affected by the petroleum solvents)
- Excellent adhesion to bituminous rolls, concrete, brickwork, cement, fibre cement, zinc, galvanised plate steel, etc.

TECHNICAL CHARACTERISTICS	
Base	Bitumen, rubber, polymers, solvents, fibre reinforcement and adhesive additives.
Colour	Black
Consistency	Thick liquid
Drying time	Dust-free after 5 - 8 hours Dry after 24 - 36 hours depending on the coat thickness and ambient conditions. Full hardening after ± 2 to 3 weeks. Only then paint over with <b>Paraphalt Reflex</b>
Solvents	Petroleum hydrocarbons. With use take necessary elemen- tary precautionary measures.
Flash point cc : ASTM D93	42°C
Density at 20 °C	1 g/cm <sup>3</sup>
Application temperature	+5°C - +30°C
Theoretic consumption	1 <sup>st</sup> penetration coat (15% diluted) : 0,750 l/m <sup>2</sup> 2 <sup>nd</sup> coat : 1,200 l/m <sup>2</sup>
Shelf life, in unopened packing.	Min. 18 months

PACKING
12 cans 1 kg/box - 30 boxes/pallet
Can 5 kg - 96 cans/pallet
Can 10 kg - 44 cans/pallet
Can 25 kg - 22 cans/pallet

# **METHOD OF USE**

#### Primers

On a very porous or very dusty surface (concrete, cement, etc.) first apply a coat of **Paraphalt Primer** (drying time 30 min).

#### Application

- Ready for use
- Apply with a paintbrush, brush, rubber squeegee or airless on clean, dust- and grease-free, preferably dry surface (two crossed coats).
- Brush Paraphalt Liquid into blisters and bursts (first puncture), fill with Paraphalt repair paste and then treat the whole surface

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.



- Dilute with white spirit in cold weather and for the first penetration coat
- Sunlight can cause ageing symptoms in the surface; this is prevented by, after complete drying, shielding the **Paraphalt** Liquid coat with a silver-coloured sun-reflecting finishing coat **Paraphalt Reflex**

#### Cleaning

Clean tools with white spirit.

## SAFETY

Safety data sheet available on request.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.



DL Chemicals nv Roterijstraat 201-203 - Zone 5 Snepbeek - 8793 Waregem - Belgium T +32 56 62 70 51 - F +32 56 60 95 68 info@dl-chem.com - www.dl-chem.com