



## CHARACTERISTICS

- Contact glue based on poly-chloroprene and high quality resins in a mixture of organic solvents
- Designed for vertical gluing
- Without dripping or smudging.
- Thixotropic paste
- Great adhesion
- Indoor use

## APPLICATIONS

- Is used on laminated or stratified panels, rubber or plastic selectionnals, wood, veneering, agglomerates, plywood, fibro-cement, metals, cork, phenolic foam, polyurethane, pasted materials on concrete, asbestos cement, plaster on metal, or combination of any of these elements.

TECHNICAL CHARACTERISTICS	
Colour	Brown-beige
Viscosity	Thixotropic
Inflammability	Yes
Density at 20°C	0,88 g/cm <sup>3</sup>
Temperature resistance	85°C
Shelf life, in the original packing between 15°C and 20°C. In case of seepage or condensation, pour out few drops of solvent from the surface. This operation does not bring any damage to the quality of the product.	Min. 18 months
Consummation	200 - 350 g/m <sup>2</sup>
Application temperature	> 10°C

PACKING
12 cans of 750 ml/box - 50 boxes/pallet
Can 5 l - 108 cans/pallet

## METHOD OF USE

### Preparation

Surfaces must be dry, free of dust and any contaminating substances.

### Application

- Spread The glue with a brush or a spatula.
- Spread a smooth layer of glue (150 g) on the two surfaces to be bonded.
- Let solvents escape (7 to 15 min. according to temperature and surfaces).
- The elements to be glued can be pressed together as soon as the glue does not stick to the fingers anymore.
- Press the two parts together very precisely as the setting power is immediate and irreversible. After the pressing it is no longer possible to correct
- Maximum adherence is achieved after 48 to 72 hours.

### Cleaning

With acetone

## SAFETY

Safety data sheet available on request

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

## LIMITATIONS

This glue cannot be used with polystyrene.

## TECHNICAL APPROVALS



\* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.