



### CHARACTERISTICS

- Epoxy-ester-based zinc spray
- Outstanding cathodic corrosion prevention
- Fast curing
- Weather resistant
- Heat resistance up to 350°C
- Excellent adhesion

### APPLICATIONS

- To treat and protect galvanised and untreated steel
- Protection of welding seams, cutting edges and reparation spots
- Appropriate for use in the automotive industry, metal industry, HVAC, trailer and container construction...

TECHNICAL CHARACTERISTICS	
Base	Ester d'époxy
Colour	Grey
VOC content	± 54%
Dry matter	+/- 46%
Yield	1,25 - 1,75 m <sup>2</sup>
Dust free	After 10 - 15 min
Dry to the touch	After 20 - 30 mi
Completely dry	After 24 h
Processing temperature	15°C - 25°C
Heat resistance	Up to 350°C

PACKING AND COLOURS
6 spray cans of 400 ml/box
Grey

### METHOD OF USE

#### Preparation

Please read the instructions on the can before use. All surfaces should be dry, clean and free from dust or grease. All traces of rust or paint should be removed. The surface should be sanded, cleaned and dried.

#### Application

- Shake the can during 2 minutes and test before use
- Spray at a distance of 25 - 30 cm. Apply in different layers
- Before applying another layer, shake the can again
- Dry after 24 hours. After drying, a primer layer and finishing layer can be applied if desired
- After use the can should be turned upside down completely and spray a few seconds to clean the valve

### SAFETY

Safety data sheet available on request.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.